




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B32B	A2	(11) International Publication Number: WO 00/32388 (43) International Publication Date: 8 June 2000 (08.06.00)
<p>(21) International Application Number: PCT/US99/27275</p> <p>(22) International Filing Date: 16 November 1999 (16.11.99)</p> <p>(30) Priority Data: 60/108,541 16 November 1998 (16.11.98) US Not furnished 12 November 1999 (12.11.99) US</p> <p>(71) Applicant (for all designated States except US): JOHNS MANVILLE INTERNATIONAL, INC. [-/US]; 717 Seventeenth Street, Denver, CO 80202 (US).</p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): FAY, Ralph, Michael [-/US]; 2249 South Hoyt Court, Lakewood, CO 80227 (US). WULLIMAN, Rebecca, Sue [-/US]; 6589 East Lake Place, Englewood, CO (US). STACY, James, Walter [-/US]; 20770 Oasis Avenue, Peyton, CO 80831 (US). TOWNSEND, Jeffrey, Canon [-/US]; 8423 South Tanglewood Street, Highlands Ranch, CO 80126 (US). VOLENEC, Steven, N. [-/US]; 7553 South Willow Circle, Englewood, CO 80112 (US).</p> <p>(74) Agent: TOUSLEE, Robert, D.; Johns Manville Corporation, 10100 West Ute Avenue, Littleton, CO 80127 (US).</p>		<p>(81) Designated States: AU, BR, CA, CN, DE, DK, ES, GB, JP, LU, RU, SE, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published Without international search report and to be republished upon receipt of that report.</p>
<p>(54) Title: BURN THROUGH RESISTANT SYSTEMS FOR TRANSPORTATION, ESPECIALLY AIRCRAFT</p> <p>(57) Abstract</p> <p>An encapsulated insulation composite system for increasing the burn through resistance of an aircraft fuselage includes: an insulation layer of glass fiber or foam insulation and a coating or interleaf barrier layer of a high temperature resistant material and/or a coating or barrier layer of a high temperature resistant material on an outer major surface of the insulation layer of the composite and a film encapsulating the composite. Preferably, the barrier layer or layers include a reflective mineral, such as a reflective mineral containing coating carried on a sheet material. Preferably, the encapsulating film is a polymeric film such as a polyimide film.</p> 		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**BURN THROUGH RESISTANT SYSTEMS FOR TRANSPORTATION,
ESPECIALLY AIRCRAFT**

5

This application claims priority to provisional application Serial No. 60/108,541, filed November 16, 1998, the disclosure of which is fully incorporated herein.

BACKGROUND OF THE INVENTION

10 The present invention relates to an insulation system for aircraft fuselages and, in particular, to an insulation system for increasing the burn through resistance of aircraft fuselages to provide passengers with additional time within which to evacuate an airplane in the event of an external fuel fire.

15 Currently, the Federal Aviation Administration (the FAA) is testing various aircraft fuselage sidewall constructions to determine if they can demonstrate a significant increase in burn through resistance in a simulated exterior fire condition. For example, the test simulates a situation where the aircraft is on the ground and a jet fuel fire ignites next to the outside of the fuselage.

20 The baseline fuselage sidewall construction in current use combines an interior trim panel with one or more layers of Microlite AA fiberglass insulation blanket, encapsulated in a reinforced Mylar film, that is positioned in the framework of an aircraft with an exterior aluminum skin. The fiberglass blanket currently used in the baseline construction is 0.42 pound per cubic foot (pcf) X 1 inch ($6.7\text{Kg/m}^3 \times 25.4\text{mm}$) or 0.6 pcf X 1 inch ($9.6\text{Kg/m}^3 \times 25.4\text{mm}$) Microlite AA. In some constructions used by aircraft manufacturers, one or all of the Microlite AA fiberglass blanket layers are replaced with a 0.3 pcf X 1 inch to a 0.6 pcf X 1 inch ($4.8\text{Kg/m}^3 \times 25.4\text{mm}$ to $9.6\text{Kg/m}^3 \times 25.4\text{mm}$) polyimide foam.

25 In a real or simulated fire condition, all of the individual fuselage components melt away quickly and permit flame to penetrate into the passenger compartment. The baseline fuselage construction typically provides only a couple of minutes of burn through protection in these tests. There are many ways to improve burn through protection in an aircraft fuselage. However, the most obvious solutions require a significant addition of weight which is undesirable in aircraft construction.

SUMMARY OF THE INVENTION

By replacing the current two to three layers of 0.42 pcf X 1 inch ($6.7\text{Kg/m}^3 \times 25.4\text{mm}$) or 0.6 pcf X 1 inch ($9.6\text{Kg/m}^3 \times 25.4\text{mm}$) Microlite AA blanket insulation system, described above, with the burn through resistant system of the present invention, the length of time it takes to burn through the insulation portion of the system has been shown to increase from a couple of minutes to more than five minutes and preferably more than 7 minutes. The burn through resistant system of the present invention has one or more coating or interleaf layers of high temperature resistant material included in the encapsulated multilayered construction of fiberglass blanket layers and/or foam insulation layers.

To provide good results in the simulated fire condition of a full scale FAA simulated burn through test, the system must also be able to withstand moderate air pressure fluctuations attributed to the pulsing flame front or wind. The burn through resistant system of the present invention is able to withstand such moderate air pressure fluctuations.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic cross section through a first embodiment of the burn through resistant system of the present invention installed in a fuselage with one coating or interleaf layer of high temperature resistant material intermediate insulation layers of the system.

FIG. 2 is a schematic cross section through a second embodiment of the burn through resistant system of the present invention installed in a fuselage with two coating or interleaf layers of high temperature resistant material intermediate insulation layers of the system.

FIG. 3 is a schematic cross section through a third embodiment of the burn through resistant system of the present invention installed in a fuselage with a coating or interleaf layer of high temperature resistant material among an insulation layer and the encapsulating envelope of the system.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

As shown in FIG. 1, a first embodiment of the burn through resistant system 20 includes a plurality of glass fiber insulation blanket layers and/or foam insulation sheet layers 22 and one high temperature resistant material coating or interleaf layer 24 intermediate two of the insulation layers 22. The glass fiber insulation blanket layers and/or foam insulations sheet layers 22, along with the high temperature resistant material coating or interleaf layer 24, are encapsulated or enclosed within an envelope 26 and placed against or adjacent the skin 28,

e.g. aluminum skin, of the aircraft fuselage 30. As shown in FIG. 2, a second embodiment of the burn through resistant system 20 includes a plurality of glass fiber insulation blanket layers and/or foam insulation sheet layers 22 and two high temperature resistant material coating or interleaf layers 24 which are each located intermediate two of the insulation layers 22. The glass fiber insulation blanket layers and/or foam insulations sheet layers 22, along with the high temperature resistant material coating or interleaf layers 24, are encapsulated or enclosed within an envelope 26 and placed against or adjacent the skin 28, e.g. aluminum skin, of the aircraft fuselage 30. In both of the embodiments shown, the major surfaces of the insulation layers 22 and the coating or interleaf layers 24 extend in planes parallel to or substantially parallel to each other and the major surfaces of the skin 28. The systems of FIGS 1 and 2 could include additional insulation layers 22 and high temperature resistant material coating or interleaf layers 24.

In the embodiment of the burn through resistant system 20 shown in FIG. 3, the system 20 includes a plurality of glass fiber insulation blanket layers and/or foam insulation sheet layers 22; a first high temperature resistant material coating or interleaf layer 24 located intermediate one of the insulation layers 22 and the envelope 26 on the outer or fuselage skin facing side (the flame facing side) of the system; and a second high temperature resistant material coating or interleaf layer 24 located intermediate two of the insulation layers 22. An envelope 26 encapsulates or encloses the insulation layers 22 and coating or interleaf layers 24. The system 20 is placed against or adjacent the skin 28, e.g. aluminum skin, of the aircraft fuselage 30 with the portion of the envelope covering the first coating or interleaf layer 24 of high temperature resistant material adjacent the skin 28 of the aircraft. As with the embodiments of FIGS. 1 and 2, the major surfaces of the insulation layers 22 and the coating or interleaf layers 24 extend in planes parallel to or substantially parallel to each other and the major surfaces of the fuselage skin 28. While not shown in FIG. 3, additional coating or interleaf layers 24 of high temperature resistant material can be included intermediate the insulation layers 22.

Preferably, the glass fiber blanket layers 22 are one inch (25.4mm) thick Microlite AA glass fiber insulation blankets (manufactured and sold by Johns Manville International, Inc.) having densities of about 0.42 pcf (6.7Kg/m³) or one inch (25.4mm) thick Premium NR glass fiber insulation blankets (manufactured and sold by Johns Manville International, Inc.) having densities of about 0.34 pcf (5.4Kg/m³). Preferably, the foam insulation layers 22 are one inch (25.4mm) thick polyimide foam insulation layers having densities of about 0.3 pcf (4.8Kg/m³) to about 0.6 pcf (9.6 Kg/m³).

Preferably, the high temperature resistant coating or interleaf layer or layers 24 include a reflective plate-like mineral, such as but not limited to vermiculite, applied in a coating to or incorporated into one or both major surfaces of a sheet, such as a paper sheet, an organic fiber mat, a glass fiber mat, or a fabric sheet. The high temperature resistant coating or interleaf layers 24 can also be applied as a coating directly to one or more of the major surfaces of the insulation layers 22. One example of an interleaf layer 24 includes a paper like product, such as Manninglas 1208 paper (manufactured by Lydall Corporation) made from 6.5 micron DE glass (little or no binder is used to produce the paper) and vermiculite which is applied as a coating on one or both sides or major surfaces of the paper sheet. An interleaf layer 24 of Manninglas 1208 paper coated on both sides weighs 13.8 g/ft² (148g/m²). An insulation system 20 using three layers 24 of 0.34 Premium NR fiber glass blanket to sandwich two layers of Manninglas 1208 paper weighs about 66 g/ft² (710g/m²) (the weight of the aluminum fuselage skin is not included). Another example of an interleaf layer 24 includes a spunlaced fabric, such as Freudenberg C1999VM aircraft seat cushion fire block fabric made from 70% Curlon partially oxidized PAN fiber and 30% Kynar phenolic fiber and zig-zag stitched with a high temperature resistant organic fiber, and vermiculite which is applied as a coating to one or both sides or major surfaces of the fabric. A burn through resistant system 20 of the present invention using one interleaf layer of Freudenberg C1999VM fabric coated with a vermiculite coating and sandwiched between two outboard fiber glass or polyimide foam layers 22 is considered tough enough to withstand the air pressure fluctuations attributed to a pulsing flame front or wind and provides greater than 7 minutes of burn through resistance. This embodiment of the system 20, using three layers 22 of 0.42 pcf (6.7Kg/m³) Microlite AA glass fiber blanket and one interleaf layer 24 of vermiculite coated Freudenberg C1999VM fabric weighs about 62.5 g/ft² (672g/m²) (the weight of the aluminum fuselage skin is not included). Due to the desire to keep aircraft fuselages as light as practical, the systems 20 of the present invention preferably weigh less than 70 g/ft² (753g/m²) not including the weight of the fuselage skin.

Preferably, the encapsulating envelope 26 is a polymeric film envelope, such as but not limited to a Mylar film or a polyimide film envelope with a polyimide film envelope being preferred since the use of such an envelope extends the burn through time when compared to a Mylar film envelope. Two burn through resistant systems were tested using the same core materials, but with different film envelopes. A three layer system of 0.42 pcf (6.7Kg/m³) Microlite AA glass fiber blankets was tested with a Mylar film covering and also with a polyimide film covering (System configuration I). A three layer system of ANSC carbon fiber blanket and two layers of

0.42 pcf (6.7Kg/m³) Microlite AA glass fiber blankets was also tested with a Mylar film covering and also with a polyimide film covering (System configuration II). With System configuration I, the burn through time using the Mylar film covering was about 2.67 minutes and the burn through time using the polyimide film covering was about 3.25 minutes. With System configuration II, the burn through time using the Mylar film covering was about 4.25 minutes and the burn through time using the polyimide film covering was about 8.50 minutes. Thus, in both tests, the system covered with the polyimide film exhibited a longer burn through time.

The term "burn through time" as used in this specification and claims relates to a test method developed by Johns Manville International, Inc. and is based on an ASTM E-119 test rig. This ASTM test method is a standard one for fire tests of building construction and materials. The test sample is 73.7 cm X 73.7 cm square and is tested in a vertical configuration. The sample itself is made up of a "system" consisting of a 1.6 mm thick aluminum skin to the fire side and the insulation batting enclosed in covering films of various types. The sample does not include an interior trim panel as part of the fuselage construction. The system sample is subjected to a furnace with a heat flux of 12 to 15 W/cm² and a temperature of 1093°C. The test begins when a sliding door separating the furnace from the system test sample is removed. The time of failure back to the back or cold side covering film is recorded, and the "burn through time" is deemed to be when the flame reaches or penetrates to the cold side.

Initial test results from this method showed that aluminum skin on its own achieved an approximate failure time of one minute. The standard configuration of three layers of 0.42 pcf (6.7Kg/m³) Microlite AA glass fiber blanket encased in Mylar film (System configuration I) yielded a result of 2.67 minutes to burn through. A system consisting of a layer of carbon fiber batting and two layers of fiber glass encapsulated in polyimide film (System configuration II) yielded a burn through time of 8.55 minutes in the above described Johns Manville International, Inc. test apparatus. These results show good relative ranking with the full scale FAA results for burn through time.

The system 20 of the present invention preferably has a burn through time of at least 5 minutes and more preferably, 7 minutes. A system 20 of the present invention including three insulation layers 22 of 0.42 pcf X 1 inch (6.7Kg/m³ X 25.4mm) Microlite AA glass fiber blanket and two interleaf layers 24 of 40 mil Manninglas 1208 glass fiber mat coated on both sides with vermiculite, encapsulated within AN47R Mylar film, exhibited a burn through time of greater than 10:00 minutes (film failure at 5:00 minutes; test stopped after 10:00 minutes). A system 20 of the present invention including two outer insulation layers 22 of 0.42 pcf X 1 inch (6.7Kg/m³ X

25.4mm) Microlite AA glass fiber blanket, an intermediate layer 22 of 0.3 pcf X 1 inch (4.8Kg/m^3 X 25.4mm) Aero-mide polyimide foam and two interleaf layers 24 of 40 mil Manninglas 1208 glass fiber mat coated on both sides with vermiculite, encapsulated within AN47R Mylar film, exhibited a burn through time of 10:00 minutes (film failure at 4:38 minutes; excessive smoke from foam; test stopped after 10:00 minutes). A system 20 of the present invention including three insulation layers 22 of 0.42 pcf X 1 inch (6.7Kg/m^3 X 25.4mm) Microlite AA glass fiber blanket and two interleaf layers 24 of .015 inch (0.38mm) Manninglas 1208 glass fiber mat knife coated with vermiculite, encapsulated within Insulfab 240 Mylar film, exhibited a burn through time of greater than 10:00 minutes (film failure at 3:54 minutes; standard smoke; glowing mat at 5:21 minutes; test stopped after 10:00 minutes). A system 20 of the present invention including two outer insulation layers 22 of 0.42 pcf X 1 inch (6.7Kg/m^3 X 25.4mm) Microlite AA glass fiber blanket, an intermediate layer 22 of 0.3 pcf X 1 inch (4.8Kg/m^3 X 25.4mm) Aero-mide polyimide foam and two interleaf layers 24 of .015 inch (0.38mm) Manninglas 1208 glass fiber mat knife coated with vermiculite, encapsulated within an Insulfab 240 Mylar film, exhibited a burn through time of greater than 10:00 minutes (film failure at 4:04 minutes; medium smoke; glowing mat at 6:10; test stopped after 10:00 minutes). A system 20 of the present invention including three insulation layers 22 of 0.42 pcf X 1 inch (6.7Kg/m^3 X 25.4mm) Microlite AA glass fiber blanket and two interleaf layers 24 of Freudenberg C1999VM 200 grams/m² fabric coated with vermiculite, encapsulated within Insulfab 240 Mylar film, exhibited a burn through time of 10:24 minutes (film failure at 7:40 minutes; glowing mat exposed at 8:21 minutes; test stopped after 10:24 minutes).

In describing the invention, certain embodiments have been used to illustrate the invention and the practices thereof. However, the invention is not limited to these specific embodiments as other embodiments and modifications within the spirit of the invention will readily occur to those skilled in the art on reading this specification. Thus, the invention is not intended to be limited to the specific embodiments disclosed, but is to be limited only by the claims appended hereto.

What is claimed is:

1. An insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, comprising:

an encapsulated multilayered insulation composite; the multilayered insulation composite including a first insulation layer, a second insulation layer, and a first interleaf layer of a high temperature resistant material; the insulation layers and the interleaf layer each having major surfaces extending in planes substantially parallel to each other and being enclosed within a film.

2. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 1, wherein:

the interleaf layer comprises a reflective mineral.

3. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 2, wherein:

the interleaf layer comprises a reflective mineral coated sheet.

4. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 2, wherein:

the insulation layers are glass fiber insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

5. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 4, wherein:

the polymeric film is a polyimide film.

6. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 4, wherein:

the multilayered insulation composite has a burn through time of at least 5 minutes.

7. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 2, wherein:

the insulation layers are polyimide foam insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

8. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 7, wherein:

the polymeric film is a polyimide film.

9. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 7, wherein:

the multilayered insulation composite has a burn through time of at least 5 minutes.

10. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 2, wherein:

the first interleaf layer is intermediate the major surfaces of the first and second insulation layers which are opposed to each other.

11. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 10, wherein:

the multilayered insulation composite includes a third insulation layer and a second interleaf layer of a high temperature resistant material; the third insulation layer and the second interleaf layer each have major surfaces extending in planes substantially parallel to the major

surfaces of the first and second insulation layers and the first interleaf layer; and the second interleaf layer is intermediate the major surfaces of the second and third insulation layers which are opposed to each other.

12. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 1, wherein:

the first interleaf layer of a high temperature resistant material is intermediate an outer major surface of the first insulation layer and the film.

13. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 12, wherein:

a second interleaf layer of high temperature resistant material is intermediate the major surfaces of the first and the second insulation layers which are opposed to each other.

14. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 12, wherein:

there is a third insulation layer and a second interleaf layer of high temperature resistant material which is intermediate the opposed major surfaces of two of the insulation layers.

15. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 12, wherein:

the interleaf layer comprises a reflective mineral.

16. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 15, wherein:

the interleaf layer comprises a reflective mineral coated sheet.

17. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 12, wherein:

the insulation layers are glass fiber insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

18. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 17, wherein:

the polymeric film is a polyimide film.

19. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 17, wherein:

the multilayered insulation composite has a burn through time of at least 5 minutes.

20. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 12, wherein:

the insulation layers are foam insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

21. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 16, wherein:

the foam is a polyimide foam and the polymeric film is a polyimide film.

22. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 19, wherein:

the multilayered insulation composite has a burn through time of at least 5 minutes.

23. An aircraft fuselage having an outer skin and an insulation system for increasing the burn through resistance of the aircraft fuselage, comprising:

an encapsulated multilayered insulation composite adjacent an inner major surface of the outer fuselage skin; the multilayered insulation composite including a first insulation layer, a second insulation layer, and an interleaf layer of a high temperature resistant material; the insulation layers and the interleaf layer each having major surfaces extending in planes substantially parallel to each other and the inner major surface of the metallic skin and being enclosed within a film.

24. The aircraft fuselage according to claim 23, wherein:
the interleaf layer comprises a reflective mineral.

25. The aircraft fuselage according to claim 24, wherein:
the interleaf layer comprises a reflective mineral coated sheet.

26. The aircraft fuselage according to claim 23, wherein:
the insulation layers are glass fiber insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

27. The aircraft fuselage according to claim 23, wherein:
the insulation layers are foam insulation layers; and the multilayered insulation composite is encapsulated within a polymeric film.

28. The aircraft fuselage according to claim 23, wherein:
the multilayered insulation composite has a burn through time of at least 5 minutes.

29. The aircraft fuselage according to claim 23, wherein:
the first interleaf layer is intermediate the major surfaces of the first and second insulation layers which are opposed to each other.

30. The aircraft fuselage according to claim 29, wherein:
the interleaf layer comprises a reflective mineral.

31. The aircraft fuselage according to claim 29, wherein:
the multilayered insulation composite includes a third insulation layer and a second interleaf layer of a high temperature resistant material; the third insulation layer and the second interleaf layer each have major surfaces extending in planes substantially parallel to the major surfaces of the first and second insulation layers and the first interleaf layer; and the second interleaf layer is intermediate the major surfaces of the second and third insulation layers which are opposed to each other.

32. The aircraft fuselage according to claim 31, wherein:
the interleaf layer comprises a reflective mineral.

33. The aircraft fuselage according to claim 23, wherein:
the first interleaf layer of a high temperature resistant material is intermediate an outer major surface of the first insulation layer and the film.

34. The aircraft fuselage according to claim 33, wherein:
the interleaf layer comprises a reflective mineral.

35. The aircraft fuselage according to claim 33, wherein:
a second interleaf layer of high temperature resistant material is intermediate the major surfaces of the first and the second insulation layers which are opposed to each other.
36. The aircraft fuselage according to claim 35, wherein:
the first and second interleaf layers comprise a reflective mineral.
37. The aircraft fuselage according to claim 33, wherein:
there is a third insulation layer and a second interleaf layer of high temperature resistant material which is intermediate the opposed major surfaces of two of the insulation layers.
38. The aircraft fuselage according to claim 37, wherein:
the first and second interleaf layers comprise a reflective mineral.
39. An insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, comprising:
an encapsulated insulation composite system; the insulation composite system including at least one insulation layer, and a barrier layer of a high temperature resistant reflective mineral material; the at least one insulation layer and the barrier layer each having major surfaces extending in planes substantially parallel to each other and the composite system being enclosed within a polymeric film.
40. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 39, wherein:
the polymeric film is a polyimide film.

41. The insulation system for increasing the burn through resistance of an aircraft fuselage having an outer skin, according to claim 39, wherein:
the barrier layer comprises a reflective mineral coated sheet.

7050

FIG. 1





FIG. 2



7050.

FIG. 3

